

# BenzFlex 26 Natural Yellow Hydrophilic

## Specifications

Characteristics	Value	
Residual HEMA	0.8% Maximum	
Water Content	26.0%	
Radial/Linear Expansion	1.125	
UV Cutoff	<2% @400nm	
Refractive Index	@589nm	@546nm
20°C Wet	1.461	1.463
35°C Wet	1.461	1.463
20°C Dry	1.508	1.510
35°C Dry	1.508	1.510

## Options

Standard size	Diameter – 12.7 mm / 14.5 mm / 16.0 mm	Thickness – 2.5 mm
---------------	--	--------------------

## Machining

### Environment Control

We recommend maintaining a maximum Relative Humidity of 45% at 21 ±2°C

### Diamond Tooling

TOOLING	RADIUS (MM)	TOOLING	RADIUS (MM)
Rough	0.400	Fine	0.300

### Machining Recommendations

1st & 2nd Optics	Speed (RPM)	Feed (mm/min)	Depth (mm)
Rough	10,000	90	0.20
Fine	9,500	15	0.120

### Polishing

BenzFlex 26 Natural Yellow material can be polished using normal aqueous media tumble polishing methods. Benz R&D has developed a non-aqueous polishing method. This dry polishing technology offers the benefits of fast polishing times, excellent surface quality and very high yields. Benz Dry Polishing Technology is available to our customers as a licensed technology product. Please contact us.

## Hydration

Hydrate the lens in Borate Buffer pH 7.2 isotonic saline or similar buffered saline solution as per table below.

### Isotonic Saline:

Borate Buffer pH 7.2; 295 mOs

NaCl 8.01 grams • H3BO3 2.47 grams • Na2B4O7 . 10H2O 0.14 grams

### The procedure recommended for hydration is as follows:

- Place the dry, polished IOLs in perforated vials immersed in saline solution (a minimum of 10 ml volume per IOL is recommended) at room temperature for 24 hours with stirring.
- Replace the saline solution with fresh saline solution (a minimum of 10-ml volume per IOL is recommended) and continue to hydrate for an additional 24 hour with stirring.
- After the 48-hour hydration period, the lenses should be removed from the saline and cleaned with a lens cleaning solution (such as Bausch and Lomb lens cleaner) or a basic lab detergent (such as a solution of Tergazyme and water) use sterile technique. Once hydration and cleaning is complete, the lens power is determined by confirming Diopter and MTF using an IOLA system from Rotlex or similar measuring instrument. After measurement of each lens it is re-cleaned with lens cleaning solution and rinsed thoroughly to remove residual lens cleaner.
- Lenses are now ready for packaging and sterilization.